

Technical data sheet

Properties	Test method	Unit	ONGROFOAM ULTRA
Mechanical properties			
Density	MSZ ISO 1183	g/cm ³	0,5
Tensile strength	MSZ EN ISO 527- 1,2,	M P a	>12
Elongation at break	MSZ EN ISO 527- 1,2,	%	≈15
Modulus of elasticity	MSZ EN ISO 527- 1,2,	M P a	>750
Impact strength	MSZ EN ISO 179-2	kJ/m ²	12
Shore D	MSZ EN ISO 868	-	>40
Thermal properties			
Vicat B	MSZ EN ISO 306	°C	72
		°F	162
Linear thermal expansion coefficient	DIN 53752, ISO 11359-2	K ⁻¹ x10 ⁻⁴	0,75
Thermal conductivity	DIN 52612, MSZ EN ISO 22007	W/mK	0,08
Electronical properties			
Dielectric strength	MSZ EN 60243-1	kV/mm	13
Surface resistivity	DIN 53482	Ohm	>5x10 ¹⁴
General properties			
Fire rating	ISO 13501	-	C – s3, d0 (3-10 mm)
	DIN 4102 (D)	-	B1 (3 mm)
	BS 476-7 (GB)	-	Class 1 (2 - 10 mm)
	CSE RF 3/77 (I)	-	Class 1 (2 - 10 mm)
	NFP 92-501 (F)	-	M1 (2 – 10 mm)
	UL 94 (US)	-	V0
Water absorption	MSZ EN ISO 62	%	<1
Working temperature range	-	°C	0-60
		°F	32-140

Date: 27/06/2023

Issue: 3.

This document is valid without signature.

Ongropack Kft.

H-3711 Szirmabesenyő, Miskolci utca 19. Telefon: +36 46 574 500

E-mail: ongropack@ongropack.hu

Cégjegyzékszám: CG.05-09-002943, Közfoglalkoztatási adószám: HU-11069674



All information in this technical data sheet is based on our best knowledge and personal experience. It should be therefore only be regarded as a guide and not be taken as any form of guarantee. It is the ultimate responsibility of the user to ensure the suitability of this product for his own particular use.