

TECHNICAL DATA SHEET

Office Standard Cut-Size

Physical Parameters

	REFERENCE	TARGET	TYPICAL VALUES		
Basis Weight, g/m²	ISO 536	80.0	76.8		83.2
Thickness, µm	ISO 534	107	102		112
Stiffness MD, mN	ISO 2493-1		≥ 100		
Stiffness CD, mN	ISO 2493-1		≥ 35		
Tensile MD, kN/m	ISO 1924-2		≥ 4.7		
Bendtsen Roughness, ml/min	ISO 8791-2	180	120		240
Air Permeability, ml/min	ISO 5636-3			≤	1700
Moisture, %	ISO 287	4.0	3.5		4.5
Formation, #	Internal Method		≥ 30		

Optical Parameters

	REFERENCE	TARGET	TYPICAL VALUES		
Whiteness, CIE	ISO 11475	161	158	164	
Brightness D65, %	ISO 2470-2	110	107	113	
Opacity, %	ISO 2471	93	≥ 91		

Page:

1 / 1

Approved by:

Product Development and Technical Services: Eng. Vitor Crespo

FTP-PAP-0046 Rev.: 005 - Data: 2016/03/07 Itegelaar Printed on: 2016/09/12 08:48:18



QUALITY AND ENVIRONMENTAL INFORMATION

- The Navigator Company's papers are made from Elemental Chlorine Free (ECF) bleached kraft pulp;
- The Navigator Company's papers are produced in a neutral/slightly alkaline papermaking process, therefore considered as "acid free" products which meet the requirements of ISO 9706 standard, "Information and documentation Paper for documents Requirements for permanence";
- The Navigator Company's laboratories are accredited according to the ISO 17025 standard;
- Quality, Environmental and Safety Management Systems are certified according to the ISO 9001, ISO 14001 and OHSAS 18001 standards.
- The Navigator Company is chain-of-custody certified according to standards FSC-STD-40-004 and FSC-STD-40-005 (NC-COC-014433/NC-CW-014433) and to standard PEFC ST 2002:2013 (APCER/2007/CDR.0008).

Rev.04: - Date: 2016-02-12