

Planatol HM 55/1

Hot melt side glue based on EVA, free of fillers and pigments

Typical Application

- Side gluing in perfect-binding machines

Technical Data

Specification Values

Viscosity *
(Brookfield, DIN 53019, 170° C) 1,800 – 2,300 mPas

Softening Point (Mettler) 85 - 100 °C

*at date of production

Typical Technical Characteristics

Open time long
Color colorless to slightly yellowish translucent

Form of Delivery/Container

Granulate, 25 kg bags, further on demand

General Application Instructions

Processing

Suitable for nozzles, wheels or discs.

Processing temperatures 150 – 180 °C, 10 – 20 °C lower in the premelter.

In case of difficult substrates preliminary tests are necessary.

Please be aware that in case the working temperature will be changed all other parameters of the adhesive such as open time, viscosity and adherence will change as well. Long heating - and several preheating phases cause a gradually yellowing of the adhesive and will lead to its uselessness. Therefore it is recommended to adjust the amount of melted adhesive to the daily use.

Please Note: Hotmelts emit fumes although when the required working temperature will be observed. Nevertheless unpleasant odors will often occur. In case the stipulated working temperatures will be exceeded substantially for a longer period of time, harmful decomposition products can develop. Therefore it is necessary to take measurements to eliminate the harmful fumes, e.g. by installing a suitable extraction system as well as by cleaning the melting container and coating head in regular intervals.

Storage

Max. Processing Period: 12 Months

After delivery of the shipment the product can be consumed during the a.m. period provided that it is stored properly packed in factory sealed containers at a dry site at temperatures from 15 to 25°C. The bags must not be stacked higher than delivered by Planatol GmbH to prevent a locking of the granulate.

Planatol GmbH grants no warranty or guarantee in case the product will be used after the expiration date of the indicated processing period.

Cleaning

To avoid deposits on the melting and application equipment, we recommend cleaning with our liquid cleaner PLANATOLIN HM on a regular basis. Time intervals for cleaning have to be determined individually depending on the degree of contamination.

Planatol GmbH

Fabrikstraße 30-32 | 83101 Rohrdorf
Postfach 62 | 83099 Rohrdorf | Germany

T. +49 (0) 8031 720-0
F. +49 (0) 8031 720-180

info@planatol.de
www.planatol.de



For Your Attention:

The indicated specification values are valid for the products at the time of delivery ex works Rohrdorf. In case of doubt Planatol storage samples will be examined as sole reference. Planatol only guarantees the compliance with the specification values as indicated on the data sheet. Furthermore assurances, also orally given, are not guaranteed.

A self-test respectively a test of the adhesive regarding the purpose of application through the client is compulsory, especially testing the production conditions/substrates at the customer's site is obligatory. Recommendations given by Planatol are based on experiences and are without any obligation.

Indications made on this data sheet present no warranty of characteristic in the sense of the current Federal Supreme Court jurisdiction and are therefore not binding. Please always get in touch self-reliant with the responsible Planatol employee to receive the updated version of this data sheet or for further information concerning suitability regarding the FDA, BfR or EU guidelines.

For information regarding product safety please refer to the material safety data sheet.