

FR

Couché 2 Faces Mat à Main

Propriété			Unité	Tolérance	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Grammage	ISO 536	TAPPI T410	g/m ²	± 4%															
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Blancheur CIE	ISO 11475			± 3	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4
Opacité	ISO 2471	TAPPI T519	%	±2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Rugosité Bendtsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1.2*std	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Lissé Bekk	ISO 5627	TAPPI T479	s	±30%	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Humidité relative		TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Dernière actualisation: **24-10-14**
- Ces valeurs sont sujettes à modification sans avis préalable

EN

Coated Paper 2 Sides Bulky Matt

Property			Unit	Tolerance																
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380	
Thickness	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394	
Whiteness CIE	ISO 11475			± 3	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	
Opacity	ISO 2471	TAPPI T519	%	±2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-	
Roughness Bendtsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1.2*std	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-	
Smoothness Bekk	ISO 5627	TAPPI T479	s	±30%	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90	
Relative Humidity		TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

- Last updated: **24-10-14**
- Values are subject to change without notice.

ES

Estucado 2 Caras Mate Volumen

Propiedad			Unidad	Tolerancia	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Gramaje	ISO 536	TAPPI T410	g/m ²	± 4%															
Calibre	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Blancura CIE	ISO 11475			± 3	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4
Opacidad	ISO 2471	TAPPI T519	%	±2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Rugosidad Bendtsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1.2*std	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T479	s	±30%	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Humedad relativa		TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última actualización: **24-10-14**
- Los valores están sujetos a cambio sin aviso previo.

IT

Carta Patinata Mat ad alto spessore

Proprietà			Unità	Tolleranza																
Grammatura	ISO 536	TAPPI T410	g/m²	± 4%	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380	
Volume	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394	
Bianco CIE	ISO 11475			± 3	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	
Opacità	ISO 2471	TAPPI T519	%	±2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-	
Rugosità Bendtsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1.2*std	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-	
Liscio Bekk	ISO 5627	TAPPI T479	s	±30%	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90	
Umidità relativa		TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	

- Ultima revisione: **24-10-14**
- I valori sono soggetti a modifiche senza preavviso.

DE

2-seitig Gestrichen Matt Bilderdruckpapier

Kennzeichen			Masseinheit	Toleranz	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Grammatur	ISO 536	TAPPI T410	g/m ²	± 4%															
Dicke	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Weisse CIE	ISO 11475			± 3	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4
Opazität	ISO 2471	TAPPI T519	%	±2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Rauhigkeit Bendtsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1.2*std	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Bekk	ISO 5627	TAPPI T479	s	±30%	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Relative Feuchtigkeit		TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Letzte Änderung: **24-10-14**
- Diese Werte können ohne vorherige Ankündigung geändert werden

PT

Couché 2 Faces Mate Volume

Propriedade			Unidade	Tolerância	90	100	110	115	130	135	150	170	200	225	250	275	300	350	380
Gramagem	ISO 536	TAPPI T410	gsm	± 4%															
Calibre	ISO 534	TAPPI T411	µm	± 4%	93	104	117	123	140	147	156	182	210	236	265	297	327	392	394
Brancura CIE	ISO 11475			± 3	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4	121,4
Opacidade	ISO 2471	TAPPI T519	%	±2	92,0	93,5	94,5	95,0	96,0	96,5	97,5	98,0	-	-	-	-	-	-	-
Aspereza Bendtsen	ISO 8791-2	TAPPI UM-535	ml/min	≤1.2*std	100	100	100	100	-	-	-	-	-	-	-	-	-	-	-
Lisura Bekk	ISO 5627	TAPPI T479	s	±30%	-	-	-	-	100	100	100	100	100	100	100	100	90	80	90
Humidade relativa		TAPPI T502	%	± 7	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50

- Última atualização: **24-10-14**
- Os valores estão sujeitos a mudanças sem pré-aviso.

