



ForceTack Supreme | 51.108N

ForceTack Supreme offers exceptional adhesive strength, forming an instant bond that reduces displacement during application. Ideal for tough surfaces like low-energy plastics and powder-coated finishes, it provides long-lasting adhesion in harsh conditions such as temperature changes, humidity, UV exposure, and frequent handling.

FACE FILM

Polymeric PVC, matt white

Thickness (µm)	80
Opacity	High

ADHESIVE

Clear synthetic rubber-based acrylic, high tack permanent

Thickness (µm)	50
Adhesion to steel	FINAT FTM 1
20 minutes (180°) N/25mm	37
24 hours (180°) N/25mm	38
Adhesion to powder coated surfaces	FINAT FTM 1
20 minutes (180°) N/25mm	39
24 hours (180°) N/25mm	40
Adhesion to polyethylene	FINAT FTM 1
20 minutes (180°) N/25mm	38
24 hours (180°) N/25mm	40

RELEASE LINER

Lay-flat kraft paper liner, double-sided PE coated

Thickness (µm)	180
----------------	-----

PRODUCT APPLICATION

Application method	Dry
Dimensional stability (.mm)	<1
Application temperature (°C)	0 to 30
Service temperature (°C)	-20 to 70



DURABILITY

Shelf life (months)	12	
Outdoor durability (years)	8	Vertical exposure, Mid-EU climate

REGULATIONS & CERTIFICATIONS

Fire Rating	EN 13501-1 (Class B)
-------------	----------------------

ROLL SIZES

1370mm x 50m

PRINTING METHOD

(Eco)-Solvent, Latex, UV

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in iSee2 material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.

